

SECTION 07 56 00
APOC GUIDE SPECIFICATION
SMOOTH AND GRANULE SURFACE ROOF RESTORATION
AM-BU-525-CGR 19

PART I – GENERAL

1.01 RELATED DOCUMENTS

- A. Requirements of Division 1 General Requirements and manufacturers guide specifications.
- B. Related sections – Sheet metal, Carpentry, Insulation and Demolition

1.02 DESCRIPTION

- A. Restoration of existing smooth surface built-up or granule surfaced modified bitumen roof membrane using a solvent based, rubberized asphalt roof coating and ceramic granule roof coating. Gravel surfaced roofs must be spudded smooth with no embedded gravel left in surface.
- B. System provides a durable waterproof membrane over existing roof surfaces that have retained structural integrity but have become weathered and deteriorated.

1.03 SUBMITTALS

- A. Sample of polyester material.
- B. Applicator approval letter from the manufacturer
- C. Product literature and flashing details
- D. Manufacturer's warranty as required

1.04 QUALITY CONTROL

- A. Comply with manufacturer's installation instructions and manufacturer's published specifications for all phases of work including substrate preparation, application of materials and protection of adjacent surfaces.
- B. All substrates must be peel tested for adhesion strength and those results provided to APOC for analysis.
- C. Insulated roofs must have an infra-red scan and wet areas marked and removed.

1.05 PRODUCT DELIVERY, STORAGE AND HANDLING

- A. Package labels must be clearly visible on pallets
- B. Store all roll goods in a dry, protected environment
- C. Store coatings and mastics at recommended temperatures appropriate for time of year materials are being installed. Product must be stored at temperatures as stated on the product label. Polyester must be kept dry.

1.06 PROJECT CONDITIONS

- A. Roof surface must be dry with no precipitation in the forecast for the next 12 hours.
- B. Contractor must follow local, state and federal codes and safety requirements

1.07 WARRANTY

- A. Warranty issued shall be for coating application only. This warranty does not cover the existing roof, structural deck or any labor associated with this project.
- B. Warranties will be issued for completed projects on entire building.
- C. For M&L Warranties, Intent to Install (form #22), job site photographs and specifications must be submitted to APOC via Fax to (813) 342-3823 a minimum of 5 working days prior to the start of the roofing project. Installing contractor MUST be an APOC Approved Contractor. Material and Labor Warranties may be available after project inspection and review of submitted reports.
- D. No APOC field representative has the authority to change the requirements for submissions or Approved Contractor Status if Material and Labor warranties are required.

PART II – PRODUCTS

2.01 ACCEPTABLE MANUFACTURERS

- A. APOC Roofing Systems

2.02 MATERIALS

- A. Roof Restoration System: AM-BU-525-CGR 19
- B. Material quantities:

APOC #525 base	5 gals per sq
APOC #525 surface coating	1.0 - 1.5 gals per sq
APOC #11 ceramic granules	60 – 80 lbs per sq

- C. APOC #11 ceramic granules
 - D. APOC #483 polyester for flashing reinforcement
 - E. APOC #482F polyester for field application
 - F. APOC #133 flashing cement for flashing and details
 - G. APOC INCREDIBLE FleeceTop tape for flashing and details
 - H. APOC #1 Green Seal sealant
 - I. APOC #525 Rubberized asphalt roof coating 6 – 6.5 gals per sq total.
- | | |
|--------------------------|-----------------|
| Weight | 7.9 lbs/gallon |
| Residue by evaporation | 60% |
| Elongation | 2000% |
| Tensile Strength | 200 psi |
| Skin time | 4-8 hours |
| Ambient application temp | 40°F - 110°F |
| Clean-up product | Mineral Spirits |

PART III – EXECUTION

3.01 INSPECTION

- A. Evaluate condition of existing smooth BUR or Mod Bit membrane system. Perform total inspection of all roof areas.
- B. Nondestructive testing (Infra-red photography and onsite inspection) shall be performed and verified with actual roof cores. A roof plan shall be made to show all wet areas, which require replacement of wet insulation and damaged membrane.
- C. Deck replacement – as the restoration progresses deteriorated deck shall be removed and replaced with like kind and quality material.
- D. All roofs must maintain positive drainage. Ponding water is defined by the NRCA as “water that remains more than 48 hours after precipitation has stopped.” Drainage can sometimes be improved by adding drains, changing the slope of the structural deck or removing existing insulation and roof membrane and reinstalling a tapered insulation and new roof membrane.

3.02 WEATHER CONDITIONS & TEMPERATURE REQUIREMENTS

- A. Ambient air temperature must be between 40°F and 110°F for application of APOC#525 rubberized asphalt roof coating. See

individual label instructions. Do not apply materials when roof surface temperature is over 180°F.

- B. When installing the coatings, roof surface must be dry with no precipitation in the forecast for the next 12 hours.
- C. Extra caution is needed when applying material in windy conditions. Never apply material with excessive wind. Contractor should constantly monitor wind direction to prevent coating of cars and adjacent surfaces. If winds become excessive, application should stop. APOC #525 can be applied by squeegee and back roller or brush.

3.03 SURFACE PREPARATION & REPAIRS

- A. Surface shall be swept clean of all debris and power washed before making repairs. Surface must be completely dry before applying repair products or coatings.
- B. Splits and blisters in membrane: Install a 5 course application of APOC #483 polyester and APOC #133 flashing cement. Apply a minimum of 1/8" thick, per ply, per layer.
- C. Wrinkles, ridges & fishmouths in membrane: Install a 3 course application of APOC #483 polyester and APOC #133 flashing cement. Apply a minimum of 1/8" thick, per ply, per layer.
- D. Abandoned pipes and vent stacks should be removed and holes filled in and roofed with like decking, insulation and membrane.
- E. Deteriorated pipe and vent flashing should be replaced with new 24-gauge galvanized flashings or appropriate metal flashing boots.
- F. Existing pipes and vents shall be cleaned and 5 coursed with APOC #133 flashing cement using a wrap and target reinforcement of APOC #483 polyester or APOC Incredible Fleece Top tape as the wrap portion and APOC #483 as the target. 60 lbs of APOC #11 ceramic granules may be embedded into a surface coat of APOC #525 rubberized asphalt roof coating or #133 flashing cement to match the color of adjacent structures and coatings. 5 course application must be installed BEFORE application of #525 rubberized asphalt coating.
- G. Curbs, base flashing, and wall flashing up to 12" high (Including Skylights, HVAC, fan, evaporator, equipment and pipe support curbs): Install a 3 course application of APOC #483 polyester in 4 gallons per square of APOC #133 flashing cement and allow to completely cure. Polyester (min. 6" width) shall extend a minimum of 6" past the cant or corner on the horizontal. Brush in the polyester to assure no voids, wrinkles or fishmouths.

- H. Metal edge: Re-secure loose metal, clean and allow to completely dry. Apply six inch wide APOC #483 polyester and coat with APOC #133 flashing cement.
- I. Scuppers: Clean, let dry and install a 3 course application of 6" APOC #483 polyester reinforcement and APOC #133 flashing cement. Three course application MUST be installed before application of #525 rubberized asphalt roof coating.
- J. Josam Type Cast Iron Drains: Remove flashing ring, clean 4'X4' area and allow to completely dry. Apply and roll in a layer of APOC Incredible Fleece Top tape over the joint at the drain bowl. Extend tape a minimum of 1" on to the cast iron drain bowl and 3" on to the existing membrane. Embed a 2'X2' piece of APOC #483 Polyester Reinforcement in a 3-4 gallon application of APOC #133 flashing rubberized asphalt roof coating and extend past drain ring down into the drain bowl. Reinstall flashing ring after application of field system is complete. Work with owner's rep to arrange for water testing of drains and drain pipes.
- K. Pitch pans: clean all exposed metal inside and out, fill and trowel to create a slight slope with APOC #1 Green Seal sealant. New or replacement pitch pans may be filled with quick drying concrete grout to two inches from the top, then fill with APOC #1 Green Seal.
- L. Wood blocking: remove and replace existing wood blocking with redwood or pressure treated 2X4 lumber for small pipes and 4X4 blocking for small HVAC units. Install blocks in APOC #133 asphalt cement on top of 1/2" Dek-Top Walkway Pads. Install new restoration membrane before installing roof walkway pads. For large horizontal gas lines and electrical conduit (2" diameter and larger), satellite dishes over 3' in diameter and HVAC units over 200 lbs. consult a structural engineer to design appropriate support system. Flash new steel supports with APOC #133 asphalt cement and APOC #483 polyester reinforcement using a wrap and target method to assure a 5 course reinforcement at the base of the penetration.
- M. Valleys and Waterways: Embed one ply of APOC #482F polyester in a 4 gal/sq application of APOC #525 and allow to fully cure.
- N. Gutters: Re-secure gutter joints, clean and prime joints using APOC Incredible primer. Seal joints by applying APOC incredible Fleece Top Tape. Coat tape and seal tape edges with APOC #1 Green Seal sealant. Deteriorated sections of metal gutter must be replaced. Rotted concealed wood gutters must be repaired and relined with a multi ply modified bitumen membrane. Water test gutters after all repairs have been completed.
- O. Metal Counter Flashing: Raise or remove existing metal counter flashing. Install specified base flashing. Reinstall metal so that

base flashing is counter flashed. On masonry walls, rake out the reglet joint and re-caulk with an APOC approved non staining sealant. On structural concrete, reseal between metal and concrete wall using an APOC approved sealant. On curbed HVAC units, reinstall metal counter flashing and seal between the unit and the counter flashing metal with a self-adhering, compressible foam tape.

- P. Expansion Joints and Control Joints: use curb flashing repair methods on the joint curbs only. Do not coat expansion or control joints with curb flashing materials. If existing expansion joint materials are repairable use materials and methods recommended by the original manufacturer of the joint. Replace the joint if deteriorated with a new expansion joint system, which will counter flash the APOC base flashing.

3.04 MEMBRANE APPLICATION

- A. Protection and start-up procedures
 1. Prior to application, post notices a minimum of 48 hours around building and parking lots. Protect adjacent surfaces where product is not to be applied using masking tape, plastic / paper sheets, stretch wrap, tarps or plywood, whichever is appropriate.
 2. Owner should be notified of start times so that fresh air intakes may be sealed off and or HVAC units shut down.
 3. Contractor must remove drain screens and seal the drainpipe to prevent plugging of drain during the coating operation. Unplug drains and reinstall screens after application operation has been completed.
- B. Base Coat: Apply APOC #525 rubberized asphalt roof coating at the rate of 5 gallons per square.
- C. Finish Coats: After #525 base coat has cured a minimum of 15 days, apply a coat of APOC #525 at the rate of 1.0 to 1.5 gallons per square and immediately broadcast APOC #11 granules at the rate of 60 – 80 lbs per square.

Note: NEVER apply to wet or damp or rusted surfaces. Surfaces should be completely cleaned before application. High humidity, cloud cover and low temperatures may extend curing periods. All repairs must use compatible products.

3.05 JOB SITE CLEAN UP

- A. Remove masking and protection

- B. Notify owner application is complete so HVAC vents can be opened and units restarted.
- C. Remove all roofing related trash and debris from jobsite.
- D. Dispose of containers in accordance with local regulations.

Note: APOC does not practice Engineering or Architecture. Any review of the buildings construction or inspection of roof plans or inspection of the building's structural roof deck by APOC representatives shall not constitute any warranty by APOC of such plans, specifications or construction. Any roof inspections are solely for the benefit of APOC. APOC is not responsible for the failure of previously applied coatings.