



TUFF-GRIP 30 SYNTHETIC ROOFING UNDERLAYMENT

TECHNICAL DATA SHEET



DESCRIPTION:

APOC Tuff-Grip 30 Synthetic Roofing Underlayment is a UV-stabilized polypropylene underlayment designed to shed water. It provides a secondary layer of protection against wind, moisture, and other elements and replaces the use of #15 and #30 organic roofing felt under asphalt shingles, residential metal and cedar shake roofing materials.

EXPOSURE:

APOC Tuff-Grip 30 Synthetic Roofing Underlayment resists UV degradation for up to 90 days. Roofing materials **MUST** be installed over APOC Tuff-Felt 30 Synthetic Roofing Underlayment within 90 days.

STORAGE:

Keep APOC Tuff-Grip 30 Synthetic rolls dry and protected from the weather.

CHECK FOR PROPER UNDER-DECK VENTILATION:

Tuff-Grip 30 Synthetic Roofing Underlayment retards moisture vapor movement. Humid air in the attic may therefore condense as water beneath the Tuff-Grip 30 Synthetic Roofing Underlayment, resulting in deterioration of the deck and growth of molds. A design professional must **ALWAYS** address the potential for moisture entrapment, excessive moisture build-up, and condensation. Moisture control solutions may include, but are not limited to, use of: • a continuous vapor barrier in the ceiling • soffit and ridge vents • gable vents • power vents. Be sure to review local building codes in your area for ventilation requirements.

PREPARATION:

Clean deck. Remove debris and protruding fasteners, which can damage Tuff-Grip15 Synthetic Roofing Underlayment and cause leaks. Repair and replace any damaged or rotted sections prior to installing Tuff-Grip15 Synthetic Roofing Underlayment. Deck must be dry, smooth in sound stable condition to prevent buckling of the deck and damage to roofing underlayment or primary roof cover.

APPROVALS:

CCRR-0604, Florida Building Code Approved FL47536, Certified to ASTM D8257, ICC-ES AC188, and ASTM E108 (Class A). Performance characteristics meet or exceed ASTM D4869 – Type I, II, III and IV • Performance characteristics meet or exceed ASTM D226 – Type I, II.

APPLICATION 4:12 SLOPE OR MORE.

Overlap Tuff-Grip 30 Synthetic Roofing Underlayment.

Before Fastening Overlap 3" (76 mm) at side lap. Extend Tuff-Grip 30 Synthetic Roofing Underlayment 3" (76 mm) over the preceding course. Use the lap line printed front of sheet to help align the 3" (76 mm) overlap. Overlap 6" (152 mm) at end lap. End laps should overlap a minimum of 6" (152 mm) and be offset from adjacent end laps by 3' (914 mm).

APPLICATION 2:12 SLOPE TO LESS THAN 4:12.*

Install Double Coverage Overlap a full 25.5" (648 mm) over the underlying course. Continue up the roof using a 22.5" (572 mm) exposure. Overlap 6" (152 mm) at end lap seams and offset from adjacent end laps by 3' (914 mm).

To fasten Tuff-Grip 30 Synthetic Roofing Underlayment use only plastic cap, corrosion resistant nails or staples with plastic caps. Fasten side and end lap 12" (305 mm) on center use 6" (152 mm) on center for high wind areas. Fasten in the field of the roll with two staggered rows of fasteners spaced 24" (610 mm) on center (use 12" [305 mm] on center for high wind areas)

INSTALL LEAK BARRIER. Where waterproof underlayment is needed, install APOC SB1 Ice and Water at eaves, valleys, rakes, skylights, dormers, and other vulnerable leak areas. See appropriate APOC Ice and Water published application instructions for details.

*Do Not Install On A Slope Less Than 2:12. Always follow local buildings codes for your specific region.

TYPICAL PHYSICAL & PERFORMANCE CHARACTERISTICS:

Roll Dimensions	48" x 250'
Roll Coverage	10 Squares
Rolls Per Pallet	56
Stock Code	AP-6400-30
Standard for Polymer UDL	PASS
ASTM D8257	
Tensile Strength (lbs.)	MD:110 / CD:110
ASTM D5035	
Tear Strength (lbs.)	MD:20 / CD:20
ASTM D4533	
Elongation (%)	MD:16 / CD:16
ASTM D5035	
Water Transmission	PASS
ASTM D4869	
Temperature Range	-40F to 240F
UV Exposure	90 Days
ICC-AC-207	
Fire Rating UL Class A	PASS
ASTM E108	
Nominal Thickness	> 8 mils
ASTM D1777	
Permeability	0.5 perms
ASTM E96 B	



Gardner-Gibson, Inc.
4161 East 7th Avenue
Tampa, FL 33605
1.800.237.1155
www.icpgroup.com

CCRR
#0604

FL APPROVED
47536

MEETS
ASTM D8257

ASTM E108
CLASS A APPROVED

MEETS
THE REQUIREMENTS OF
ICC-ES AC-188

